

PACIFIC MARINE & INDUSTRIAL®

P.O. Box 70520 ◇ Richmond, California, United States ◇ 94807-0520
Phone: 510-233-2310 ◇ Fax: 510-233-2322 ◇ Web: www.PacificMarine.net

Rubber Compound Specifications

Gray EPDM ASTM Designation- D2000 3BA 710 A14, C12, F19, Z1, Z2, Z3 and Z4

Property	Test Method	Gray EPDM
Min. Tensile Strength	ASTM D-412	1000 PSI
Min. Elongation	ASTM D-412	200%
Hardness- Shore A Durometer	ASTM D-412	70 +/- 5
Modulus @ 400% Elongation	ASTM D-412	300 PSI Min.
Heat Resistance	ASTM D-573 A1470h @ 212 F A1370h @ 158 F Max. Change in Hardness Max. Change in Tensile Max Change in Ult. Elongation	+ 10 Pts. -25% -25%
Compression Set	ASTM D-395 Method B B13 & Z4 22h @158 F	50% Max
Ozone Resistance	ASTM D-1171 C12 100 F @ 50 pphm	No Cracks
Water Resistance	ASTM D-471 EA14 70 h @ 212 F Z3 166 h @ 212 F	10% Max Swell
Low Temp. Brittleness	ASTM D-2137 Method A, 9.3.2 F17 Non brittle after 3 min. @ -40 F F19 Non brittle after 3 min. @ -67 F	Passes
Load Deflection	ASTM D-575 Method A Z1 20% Deflection	250 +/- 70 PSI
Tear Resistance	ASTM D-624 Z2 Die B	150 PPI Min.